





EUROWHITE®

Extra-white float glass: transparency of the highest standard



Extra-white glass: Convincing clearness.



Attractive glass values

Thickness	Light		Energy		
	Trans- mission	Reflection	Trans- mission	Reflection	Ab- sorption
3 mm	92 %	11 %	91 %	10 %	0 %
4 mm	92 %	10 %	90 %	9 %	0 %
5 mm	92 %	10 %	90 %	9 %	1 %
6 mm	92 %	10 %	89 %	9 %	2 %
8 mm	91 %	10 %	88 %	9 %	3 %
10 mm	91 %	9 %	87 %	9 %	4 %
12 mm	91 %	9 %	86 %	9 %	5 %

More than convincing in insulating glass

Insulating glass structure 4 mm / cavity 16 mm / 4 mm with argon filling, SILVERSTAR ENplus at layer position 3 in insulating glass

Exterior glass Interior glass	EUROWHITE	EUROFLOAT
	Light transmission	81 %
Colour reproduction index Ra	99	97
g value as per DIN EN 410	63 %	60 %
Ug value as per DIN EN 673	1,1 W/m ² K	1,1 W/m ² K

The technical data quoted here are up to date at the time of going to press. Date 09/2005


Unique thanks to its characteristics worth seeing

- Extra white float glass with a low iron oxide content
- Optical brilliance for more individuality and decorative design
- Attractive and very neutral optical appearance
- Increased light transmission for maximum transparency
- Considerably better colour reproduction index
- Optimised overall energy transmittance
- Improved test values for function coatings
- Problem-free handling during finishing process

Aesthetic lightness of various glass application

- Multi-layer glass structure
- Passive house glazing, Photovoltaic applications
- Product presentation in shop windows and showcases
- Art presentation in museums
- Glass furniture, designer objects and glass decoration

Comparison of colours EUROWHITE left and EUROFLOAT right



Addresses to contact

Euroglas Vertriebs-GmbH, D-52078 Aachen
Tel. ++49 [0]241/92 03 03-0, Fax ++49 [0]241/92 25 26
aachen@euroglas.com

Euroglas GmbH, D-39340 Haldensleben
Tel. ++49 [0]3904/638-0, Fax ++49 [0]3904/638-100
haldensleben@euroglas.com

Euroglas S.A., F-68490 Hombourg
Tel. ++33 [0]389/83 35 00, Fax ++33 [0]389/83 35 38
hombourg@euroglas.com

www.euroglas.com